



SECTION 1006

AGGREGATE FOR SURFACING

1006.1 Aggregate for surfacing shall be composed of durable particles of rock. When tested in accordance with AASHTO T 96, the percentage of wear shall not exceed 60. The percentage of deleterious substances shall not exceed the following values and the sum of percentages of all deleterious substances shall not exceed 12 percent.

Percent by Weight (Mass)	
Deleterious Rock and Shale	12.0
Mud Balls	5.0
Other Foreign Material	2.0

1006.2 The aggregate shall comply with the following requirements for the grade specified in the contract:

Grade	Kind of Material	Percent Passing					
		Sieve Sizes					
		1 in. (25.0 mm)	3/4 in. (19.0 mm)	3/8 in. (9.5 mm)	No. 4 (4.75 mm)	No. 10 (2.00 mm)	No. 200 (75 µm)
A ^b	Gravel	100	80-100	60 ^a	10-35	0-10
B ^b	Crushed Stone	100	65 ^a	5-25
C	Chat	100	80 ^a	45 ^a
D	Gravel	100	75 ^a	10-40
E	Gravel	100	75 ^a	10-40	0-5
F	Crushed Stone	100	75 ^a	10-30
G	Crushed Stone or Gravel	100	75 ^a	0-15

^a Indicates maximum permitted.

^b Type 1 or 2 Aggregate for Base may be used, except all material shall be in accordance with [Sec 1007](#).