



MINERAL SPIRITS AND DOUBLE BOILED LINSEED OIL MGS-92-09C

1.0 DESCRIPTION. This specification covers mineral spirits and double boiled linseed oil for surface sealing of bridge decks and other concrete structures as required.

2.0 MATERIALS.

2.1 Mineral Spirits Mineral spirits shall comply with the requirements of ASTM D 235, Type I, Class A and shall have an infrared spectrum typical of mineral spirits.

2.2 Double Boiled Linseed Oil. Double boiled linseed oil shall comply with the requirements of ASTM D 260, Type II, and shall have an infrared spectrum typical of double boiled linseed oil.

3.0 PACKAGING. The material shall be in non-returnable drums.

4.0 MARKING. The drums shall be marked with the manufacturer's name and net quantity in gallons.

5.0 SAMPLING.

5.1 The material will be sampled and tested at destination as deemed necessary by the engineer.

6.0 CERTIFICATION AND ACCEPTANCE.

6.1 The manufacturer shall submit to the engineer at destination a certification, for each shipment, stating that the material supplied complies with all requirements of this specification.

6.2 Acceptance of the material will be based on a satisfactory manufacturer's certification and on tests performed by the engineer.